

DEBASOFT SLH NEW

Fogging fast and good softening fatliquor for all type of leathers, for use in the pickle and tanning.

Descriptive properties

Composition	: Selected softening esters
Appearance	: Light beige liquid
pH (1:10)	: App. 7,0
Charge	: Anionic / Nonionic
Solubility in water	: Easily soluble in cold and warm water
Stability	: Stable to electrolytes and suitable for the prefatliquor in pickle and chrome tanning
Storage	: App. 1 year - dry storage-

Debasoft SLH New is developed for car seat leather production to meet high fogging value constraints and it provides softness and a full round handle.

When used as part of the fatliquor mixture on aniline leathers, Debasoft SLH New promotes even dyeing, without colour-bleaching. It is recommended to be used as fatliquor on white and pastel shades. Single use or as part of the fatliquor mixture on suede leathers, Debasoft SLH New will show a short, shiny nap and a strong brilliant dyeing.

The emulsion of Debasoft SLH New is stable to acids, salts and mineral tanning agents.

Debasoft SLH New can be used during pickle and chrome tanning, it has a dispersing effect on natural fat. This leads to a fine and even distribution of fat through the skin and gives an increased softness and a noticeable improvement in tear strength and tear resistance. The leather is more easy to sam and shave and the levelness of dyeing is improved. The migration of fat to the leather surface is reduced. The majority of fat is strongly bound and not extractable.

The leather will have good fastness to heat and light. Debasoft SLH New can also be used as a prefatliquor in rechroming and neutralization.

Application recipes

- Car upholstery leather up to 16%
- Upholstery leather up to 14%
- Garment leather up to 16%

Remarks

- The well-stirred fat mixture should be added to 3 times the quantity of water at 60°C.
- The product may separate under extreme cold or warm storage conditions.
- Before use, mix by stirring, pump circulation or any other suitable method at 15°C/ -25°C.

Packaging

145 kg in polyethylene drums.

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

KASIM HİLMİ UTKU HALEFİ MEHMET EROL UTKU

İstanbul Deri Organize Sanayi Bölgesi Burçak Sokak No.2 VIII Özel Parsel Tuzla - İstanbul / TÜRKİYE
Tel: +90 216 394 00 70 • Fax: +90 216 394 16 97 • info@debagkimya.com • www.debagkimya.com

