

## **EMDIRENAL PM**

Filling agent with excellent light fastness and heat resistance based on carbohydrates and albuminous compounds, it is used on its own or in combination with mineral-synthetic or vegetable tanning materials.

Descriptive propertiesAppearance: Light yellow powderpH (1:10): 5,5 - 7,0Concentration: 98 %Stability in chrome tanning floats: Stable

Because of its filling properties, Emdirenal PM is particularly suitable for loosely structured and flat raw materials. The product improves the fineness of the grain, gives firmer and fuller, round handle.

One possibility of application is in the cationic retanning in combination with mineral tanning salts before the neutralization. Used in the anionic retanning Emdirenal PM is combined with synthetic and vegetable tanning agents. The good filling effect of Emdirenal PM improves the buff ability of suede and nubuk leathers.

## **Application recipes**

Sheep nappa: % based on shaved weight

In the cationic retanning 3,0 - 5,0 % Emdirenal PM 2,0 - 4,0 % Chrome tanning agent

## In the anionic retanning

3,0 - 5,0 % Emdirenal PM 2,0 - 3,0 % Synthetic retanning agent 2,0 - 3,0 % Resin

Upper leather: %based on shaved weight


- 2,0 4,0 % Emdirenal PM
- 3,0 5,0 % Synthetic retanning agent
- 3,0 5,0 % Vegetable tanning agents

**Remarks Method of diluting:** Emdirenal PM is added un-dissolved into the floats.

Packaging

20 kg in kraft bags.

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.





İstanbul Deri Organize Sanayi Bölgesi Burçak Sokak No.: 2 VIII. Özel Parsel 34956 Tuzla - İstanbul / TÜRKİYE Phone: +90 216 394 00 70 • Fax: +90 216 394 16 97 • info@debagkimya.com • www.debagkimya.com