



## **DEBASOFT BA**

## Electrolyte stable, light fast synthetic softening auxiliary.

**Descriptive properties** 

**Composition**: Sulphated fatty alcohol derivatives

Appearance : Clear liquid pH (1:10) : App. 7,0 Charge : Anionic

Solubility in water : Easily soluble in cold and warm water

**Stability** : Stable to electrolytes, mineral tanning agents, acids and bases under

normal tannery conditions.

**Storage**: App. 2 years - dry storage-

Debasoft BA imparts even fat distribution through the cross section of the leather. In the production of soft, light chrome leather with good tear strength, combined with or alone one can use it during soaking, degreasing, pickling, rewetting, chrome tanning and fatliquoring.

When Debasoft BA is added to soaking baths thanks to its fat dissolving and distributing capacity soaking and washing is greatly improved. When added to degreasing and washing baths Debasoft BA improves degreasing and much clearer pelts are obtained.

In rewetting of vegetable, wet white or chrome tanned leather shaving residues and other dirt are easily washed off and rewetting thorough out the cross section is assured.

As a part of the fat liquor mix Debasoft BA acts as an emulsion stabilizer and creates a synergistic softening effect. The leathers show mild touch and good tear resistance and the grain tightness is not affected.

## **Remarks**

The well-stirred fat mixture should be added to 3 times the quantity of water at 50°C. The product may separate under extreme cold or warm storage conditions.

Before use, mix by stirring, pump circulation or any other suitable method below 15°C / -25°C.

## **Packaging**

200 kg In polypropylene drums.

Certified to: ISO 9001: 2015 ISO 14001: 2015 ISO 45001: 2018

