

DEBASOFT STA

Special auxiliary to enhance anti static charge of the leather and regulate its internal humidity.

Descriptive properties

Composition: Isomeric polyalcohol mixture

Appearance : Colorless pH (1:10) : App. 6,5

Solubility in water : Easily soluble in cold and warm water Stability : Not stable to pickle and chrome liquors

Storage: App. 2 years - dry storage-

Debasoft STA has been developed to prevent the damage caused during mechanical operations and finishing due to insufficient and uneven conditioning. By absorbing the humidity from the atmosphere and by not letting it to evaporate Debasoft STA keeps the internal water concentration in equilibrium within leather.

Debasoft STA improves the tear and tensile strength along with grain elasticity.

Mostly encountered problems during leather production results from over drying of leathers. By keeping the internal humidity in equilibrium Debasoft STA avoids and prevents below listed problems:

- · Grain cracking and lack of grain elasticity, insufficient tear and tensile strength
- Formation of high electrostatic charge during polishing, buffing and dry shaving
- Sticking of leather surface during vacuum drying
- Formation of crispation after consecutive spray coatings
- Wrinkle formation during stocking and piling
- Uneven grain pattern after dry milling.

Garments, made of leathers treated with Debasoft STA, keep their wet touch and their softness even after long storage and exhibition.

Glycerin and other simple polyalcohols loose the humidity with the temperature increase as fast as they have absorbed, while Debasoft STA, due to its restrictive hygroscopic property, keeps the humidity within the leather at equilibrium at all circumstances.

Application recipes

We recommend 1 - 3 % together with fatliquors.

Remarks

For further information please refer to its MSDS.

Packaging

215 or 1000 kg in polypropylene drums.

The information given in this technical leaflet is offered in good faith and is based upon our knowledge and experience of the products used. The suitability of the products mentioned to obtain specific properties or effects are given without obligation or guarantee and should be fully tested by the end user and adapted to suit prevailing works conditions or other products which may be employed.

İstanbul Deri Organize Sanayi Bölgesi Burçak Sokak No.: 2 VIII. Özel Parsel 34956 Tuzla - İstanbul / TÜRKİYE Phone: +90 216 394 00 70 • Fax: +90 216 394 16 97 • info@debagkimya.com • www.debagkimya.com

Certified to: ISO 9001: 2015 ISO 14001: 2015 ISO 45001: 2018

